

Renderoc MB50

constructive solutions

High performance medium-build concrete reinstatement mortar

Uses

For the reinstatement of reinforced concrete where low permeability characteristics are required and where high compressive strength is an important consideration. Renderoc MB50 has been engineered for the repair of columns and beams but, because of its medium fresh wet density, is also suitable for soffits and other overhead repair work. The mortar can also be used for small, localised patch repairs.

Where compatibility with lower strength concrete is required, but low permeability and high-build characteristics are important, Renderoc HB40 or Renderoc HB25 should be used.

Advantages

- Medium-build applications possible while maintaining higher compressive strengths — fewer cold joints
- Acrylic polymer-modification provides extremely low permeability
- Aggregate reactivity controlled in accordance with DTP Specification for Highways Works Clause 1704.6 (1998)
- Equivalent sodium oxide content restricted to less than 3 kg/m³
- Exceptional system of shrinkage compensation provides long-term dimensional stability
- One component, pre-bagged to overcome site-batched variations
- Contains no chloride admixtures
- Galvashield XP compatible

Description

Renderoc MB50 concrete reinstatement mortar is supplied as a ready to use blend of dry powders which requires only the site addition of clean water to produce a highly consistent, medium-weight repair mortar. It gives good handling characteristics while minimising water demand. The low water requirement ensures good strength gain and long-term durability.

Where strengths below 30 N/mm² and/or higher builds are required, Renderoc HB25 should be used.

Standards compliance

Renderoc MB50 has been formulated to comply with DTP Specification BD27/86 Clause 6.

Properties

The following results were obtained at a water : powder ratio of 0.15 and a temperature of 20°C unless otherwise stated.

Test method	Typical result
Compressive strength (BS 4551: 1980 Pt 2: 1980 — dry cure):	32 N/mm ² @ 3 days 41 N/mm ² @ 7 days 50 N/mm ² @ 28 days
Flexural strength (BS 6319 Pt 3: 1990):	8.2 N/mm ² @ 28 days
Tensile strength (BS 6319 Pt 7: 1985):	3.0 N/mm ² @ 28 days
Drying shrinkage 20°C/RH55%:	< 300 microstrain @ 7 days
Coefficient of thermal expansion:	11.3 x 10 ⁻⁶ /°C
Setting time (BS 4551 Pt 14: 1980) —	
Initial set:	3 hours
Final set:	5 hours
Fresh wet density:	Approximately 1998 kg/m ³ dependent on actual consistency used
Chemical resistance:	The low permeability of Renderoc MB50 severely retards chemical attack in aggressive environments. The cured mortar is highly impermeable to acid gases, water-borne chloride ions, and oxygen

Application instructions

Preparation

Saw cut or cut back the extremities of the repair locations to a depth of at least 10 mm to avoid feather-edging and to provide a square edge. Break out the complete repair area to a minimum depth of 10 mm up to the sawn edge.

Clean the surface and remove any contamination. Where breaking out is not required, roughen the surface and remove any laitance by light scabbling or abrasive-blasting.

Oil and grease deposits should be removed by steam cleaning, detergent scrubbing or the use of a proprietary degreaser. The effectiveness of decontamination should then be assessed by a pull-off test.

Expose fully any corroded steel in the repair area and remove all loose scale and corrosion deposits. Steel should be cleaned to a bright condition paying particular attention to the back of exposed steel bars. Abrasive-blasting is recommended for this process.

Where corrosion has occurred due to the presence of chlorides, the steel should be high-pressure washed with clean water immediately after abrasive-blasting to remove corrosion products from pits and imperfections within its surface.

Renderoc MB50

Reinforcing steel priming

Apply one full coat of Nitoprime Zincrich Plus and allow to dry before continuing. If any doubt exists about having achieved an unbroken coating, a second application should be made and, again, allowed to dry before continuing.

Substrate priming

The substrate should be saturated surface dry immediately before the application of the primer i.e. it should be thoroughly saturated with clean water and any residual surface water removed prior to applying one coat of Nitobond HAR primer and scrubbing it well into the surface. Under severe drying conditions repeated soaking may be necessary to ensure the substrate is still saturated at the time of application of the primer. Renderoc MB50 can be applied as soon as the primer becomes tacky. If the Nitobond HAR is too wet, overhead and vertical build up of the Renderoc MB50 mortar may be difficult.

In exceptional circumstances, e.g. where a substrate/repair barrier is required or where the substrate is wet or likely to remain permanently damp, Nitobond EP bonding aid should be used. Contact the local Fosroc office for further information.

Mixing

Care should be taken to ensure that Renderoc MB50 is thoroughly mixed. A forced-action mixer is essential. Mixing in a suitably sized drum using an approved Renderoc Spiral Paddle in a slow speed (400/500 rpm) heavy-duty drill is acceptable for the occasional one-bag mix. Free-fall mixers must not be used. Mixing of part bags should never be attempted.

For normal applications, place 3.60 to 3.80 litres of drinking quality water into the mixer and, with the machine in operation, add one full 25 kg bag of Renderoc MB50 and mix for a minimum of 3 minutes to a maximum of 5 minutes until fully homogeneous. Note that the powder must always be added to the water.

Mixing warning

As with other 'one pack' repair mortars, Renderoc MB50 may exhibit satisfactory handling characteristics even though inadequately mixed. This will result in a significantly lower level of performance or possible failure.

Mixing instructions must be strictly adhered to with particular emphasis on the quantity of water used and the time of the mixing operation.

Application

Exposed steel reinforcing bars should be firmly secured to avoid movement during the application process as this will affect mortar compaction, build and bond.

Apply the mixed Renderoc MB50 to the prepared substrate by gloved hand or trowel. Thoroughly compact the mortar on

to the primed substrate and around the exposed reinforcement. Renderoc MB50 can be applied in sections up to 25 mm thickness in vertical locations and up to 15 mm thickness in overhead locations in a single application and without the use of formwork. Thicker sections should be built-up in layers but are sometimes possible in a single application dependent on the actual configuration of the repair area and the volume of exposed reinforcing steel.

If sagging occurs during application, the Renderoc MB50 should be completely removed and reapplied at a reduced thickness on to the correctly reprimed substrate.

Note: the minimum applied thickness of Renderoc MB50 is 10 mm.

Build-up

Additional build-up can be achieved by application of multiple layers. The final thickness is dependent on the material consistency and substrate profile.

The surface of the intermediate layers should be comb scratch-keyed and cured with Nitobond AR. Repriming with Nitobond HAR and a further application of Renderoc MB50 may proceed as soon as this layer has set.

Finishing

Renderoc MB50 is finished by striking off with a straight edge and closing with a steel float. Wooden or plastic floats, or damp sponges may be used to achieve the desired surface texture.

The completed surface should not be overworked.

Low temperature working

In cold conditions down to 5°C, the use of warm mixing water (up to 30°C) is advisable to accelerate strength development. Normal precautions for winter working with cementitious materials should then be adopted. The material should not be applied when the substrate and/or air temperature is 5°C and falling. At 5°C static temperature or at 5°C and rising, the application may proceed.

High temperature working

At ambient temperatures above 35°C, the material should be stored in the shade and cool water used for mixing.

Curing

Renderoc MB50 is a cement-based repair mortar. In common with all cementitious materials, it must be cured immediately after finishing in accordance with good concrete practice. The use of Nitobond AR, sprayed on to the surface of the finished mortar in a continuous film, is recommended.

Large areas should be cured as trowelling progresses (0.5 m² at a time) without waiting for completion of the entire area.



Renderoc MB50

In fast drying conditions, supplementary curing with polythene sheeting taped down at the edges must be used. In cold conditions, the finished repair must be protected from freezing.

Overcoating with protective decorative finishes

To limit the advance of chlorides and carbon dioxide, Fosroc recommend the use of the Dekguard* range of protective, anti-carbonation coatings. These products provide a decorative and uniform appearance as well as protecting areas of the structure which might otherwise be at risk from the environment. Dekguard products may be applied over the repair area without prior removal of the Nitobond AR curing membrane. Other curing membranes must be removed prior to the application of Dekguard products.

Cleaning

Nitobond HAR, Nitobond AR and Renderoc MB50 should be removed from tools, equipment and mixers with clean water immediately after use. Cured material can only be removed mechanically.

Equipment used with Nitoprime Zincrich Plus Plus and Nitobond EP should be cleaned with Fosroc Solvent 102.

Estimating

Supply

Renderoc MB50:	25 kg bags
Nitoprime Zincrich Plus:	1.9 litre and 800ml cans
Nitobond HAR:	5 litre drums
Nitobond AR:	5 litre drums
Nitobond EP:	4.5 kg packs
Fosroc Solvent 102:	5 and 25 litre tins

Coverage and yield

Renderoc MB50:	Approximately 14.3 litres / 25 kg bag (approximately 1.4 m ² at 10 mm thickness)
Nitoprime Zincrich Plus:	8 m ² /litre
Nitobond HAR:	3 to 4 m ² /litre
Nitobond AR:	6 to 8 m ² /litre
Nitobond EP:	10 to 11.5 m ² /pack

Notes: the actual yield per bag of Renderoc MB50 will depend on the consistency used.

Limitations

Renderoc MB50 should not be used when the temperature is below 5°C and falling. Do not mix part bags. Due to the relatively mediumweight nature of Renderoc MB50, the product should not be used in areas subjected to traffic (in these circumstances, Renderoc S should be considered). Neither should it be exposed to moving water during application. Exposure to heavy rainfall prior to the final set may result in surface scour. If any doubts arise concerning temperature or substrate conditions, consult the local Fosroc office.

Storage

Shelf Life

The product has a shelf life of 12 months from the date of manufacture if kept in dry storage in the original, unopened bags.

Storage Conditions

Store in unopened bags in cool dry internal conditions. If stored at high temperatures and/or high humidity conditions the shelf life may be reduced to less than 6 months.

Precautions

Health and safety

For further information refer to appropriate Product Safety Data Sheet.

Fire

Renderoc MB50 is non-flammable.

Nitoprime Zincrich Plus and Fosroc Solvent 102: are flammable. Keep away from sources of ignition. No Smoking. In the event of fire, extinguish with CO₂ or foam. Do not use a water jet

Flash points

Nitoprime Zincrich Plus:	41 °C
--------------------------	-------

Fosroc Solvent 102:	33 °C
---------------------	-------



Fosroc Limited

Coleshill Road, Tamworth,
Staffordshire B78 3TL. UK

www.fosroc.com

Important note

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard Conditions for the Supply of Goods and Services, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation, specification of information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance with any advice, specification, recommendation of information given by it.

Renderoc is the trade mark of Fosroc International Limited

telephone:
+44 0 (1827) 262222

fax:
+44 0 (1827) 262444

email:
uk@fosroc.com



Certificate number FM 610