



## **Sikadur®-41 CF Normal**

### 3-part thixotropic epoxy patching mortar

---

#### **Product Description**

Sikadur®-41 CF Normal is a thixotropic, three part patching and repair mortar, based on a combination of epoxy resins and special fillers, designed for use at temperatures between +10 °C and +30 °C..

---

#### **Uses**

As repair and bonding mortar for:

- Concrete elements
- Hard natural stone
- Ceramics, fiber cement
- Mortar, Bricks, Masonry
- Steel, Iron, Aluminium
- Wood
- Polyester, Epoxy
- Glass

As a repair mortar:

- Filling of cavities and voids
- Vertical and overhead use

As an abrasion and impact resistant wearing course.

Joint filling and crack sealing:

- Joint and crack arris / edge repair

---

#### **Characteristics / Advantages**

Sikadur®-41 CF Normal has the following advantages:

- Easy to mix and apply
- Suitable for dry and damp concrete surfaces
- Very good adhesion to most construction materials
- High strength
- Thixotropic: non-sag in vertical and overhead applications
- Hardens without shrinkage
- Different coloured components (for mixing control)
- No primer needed
- High initial and ultimate mechanical strength
- Good abrasion resistance
- Good chemical resistance

---

#### **Tests**

---

#### **Approval / Standards**

Testing according to EN 1504-3.

---



## Product Data

### Form

|                            |                    |               |
|----------------------------|--------------------|---------------|
| <b>Appearance /Colours</b> | Part A:            | white         |
|                            | Part B:            | dark grey     |
|                            | Part C:            | sand          |
|                            | Parts A+B+C mixed: | concrete grey |

**Packaging** 10 kg (A+B+C) Pre-batched unit, pallets of 480 kg (48 x 10 kg).

### Storage

**Storage Conditions/  
Shelf-Life** 24 months from date of production if stored properly in original unopened, sealed and undamaged packaging, in dry conditions at temperatures between +5°C and +30°C. Protect from direct sunshine.

### Technical Data

**Chemical Base** Epoxy resin.

**Density**  $1.85 \pm 0.1$  kg/l (Part A+B+C mixed) (at +23°C) (evacuated)

**Sag Flow** On vertical surfaces it is non-sag up to 20 mm thickness. (According to EN 1799)

**Layer Thickness** 60 mm max.

When using multiple units, one after the other. Do not mix the following unit until the previous one has been used in order to avoid a reduction in handling time.

**Change of Volume** Shrinkage:  
Hardens without shrinkage.

**Thermal Expansion  
Coefficient** Coefficient W:  
 $3.5 \times 10^{-5}$  per °C (Temp. range +23°C - +60°C) (According to EN 1770)

**Thermal Stability** Heat Deflection Temperature (HDT):  
HDT = +49°C (7 days / +23°C) (According to ISO 75)  
(thickness 10 mm)

## Mechanical / Physical Properties

### Compressive Strength

(According to DIN EN 196)

| Curing time | Curing temperature        |                           |                           |
|-------------|---------------------------|---------------------------|---------------------------|
|             | +10 °C                    | +23 °C                    | +30 °C                    |
| 1 day       | 13 - 23 N/mm <sup>2</sup> | 57 - 67 N/mm <sup>2</sup> | 67 - 77 N/mm <sup>2</sup> |
| 3 days      | 45 - 55 N/mm <sup>2</sup> | 74 - 84 N/mm <sup>2</sup> | 76 - 86 N/mm <sup>2</sup> |
| 7 days      | 59 - 69 N/mm <sup>2</sup> | 77 - 87 N/mm <sup>2</sup> | 77 - 87 N/mm <sup>2</sup> |

### Flexural Strength

(According to DIN EN 196)

| Curing time | Curing temperature        |                           |                           |
|-------------|---------------------------|---------------------------|---------------------------|
|             | +10 °C                    | +23 °C                    | +30 °C                    |
| 1 day       | 6 - 12 N/mm <sup>2</sup>  | 17 - 27 N/mm <sup>2</sup> | 20 - 30 N/mm <sup>2</sup> |
| 3 days      | 14 - 24 N/mm <sup>2</sup> | 21 - 31 N/mm <sup>2</sup> | 25 - 35 N/mm <sup>2</sup> |
| 7 days      | 26 - 36 N/mm <sup>2</sup> | 33 - 43 N/mm <sup>2</sup> | 33 - 43 N/mm <sup>2</sup> |

### Tensile Strength

(According to ISO 527)

| Curing time | Curing temperature        |                           |                           |
|-------------|---------------------------|---------------------------|---------------------------|
|             | +10 °C                    | +23 °C                    | +30 °C                    |
| 1 day       | 2 - 6 N/mm <sup>2</sup>   | 13 - 19 N/mm <sup>2</sup> | 12 - 22 N/mm <sup>2</sup> |
| 3 days      | 12 - 18 N/mm <sup>2</sup> | 15 - 21 N/mm <sup>2</sup> | 14 - 24 N/mm <sup>2</sup> |
| 7 days      | 13 - 19 N/mm <sup>2</sup> | 16 - 22 N/mm <sup>2</sup> | 16 - 26 N/mm <sup>2</sup> |

### Bond Strength

(According to EN ISO 4624 and EN 1542 and EN 12188)

| Time   | Temperature | Substrate      | Bond strength             |
|--------|-------------|----------------|---------------------------|
| 7 days | +10 °C      | Concrete dry   | > 4 N/mm <sup>2</sup> *   |
| 7 days | +10 °C      | Concrete moist | > 4 N/mm <sup>2</sup> *   |
| 7 days | +10 °C      | Steel          | 4 - 8 N/mm <sup>2</sup>   |
| 7 days | +23 °C      | Steel          | 13 - 17 N/mm <sup>2</sup> |

\*100% concrete failure.

### E-Modulus

Tensile:  
~ 4'000 N/mm<sup>2</sup> (14 days at +23 °C)

(According to ISO 527)

Compressive:  
~ 9'000 N/mm<sup>2</sup> (14 days at +23 °C)

(According to ASTM D695)

### Elongation at Break

0.2 ± 0.1% (7 days at +23 °C)

(According to ISO 75)

## System Information


### Application Details

|                              |                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                             |
|------------------------------|-----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| <b>Consumption / Dosage</b>  | The consumption of Sikadur®-41 CF Normal is ~ 2.0 kg/m <sup>2</sup> per mm of thickness.                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                    |
| <b>Substrate Quality</b>     | <p>Mortar and concrete must be older than 28 days (depends on minimal requirement of strengths).</p> <p>Verify the substrate strength (concrete, masonry, natural stone).</p> <p>The substrate surface (all types) must be clean, dry and free from contaminants such as dirt, oil, grease, existing surface treatments and coatings etc.</p> <p>Steel substrates must be de-rusted similar to Sa 2.5</p> <p>The substrate must be sound and all loose particles must be removed.</p>                                                                                                                                       |
| <b>Substrate Preparation</b> | <p>Concrete, mortar, stone, bricks:<br/>Substrates must be sound, dry, clean and free from laitance, ice, standing water, grease, oils, old surface treatments or coatings and all loose or friable particles must be removed to achieve a laitance and contaminant free, open textured surface.</p> <p>Steel:<br/>Must be cleaned and prepared thoroughly to an acceptable quality i.e. by blastcleaning and vacuum. Avoid dew point conditions.</p> <p>Other surfaces (polyester, epoxy, glass, ceramic):<br/>On these substrates pre-apply Sikadur®-31 CF Normal and then, "wet on wet" apply Sikadur®-41 CF Normal.</p> |

### Application Conditions / Limitations

|                                   |                                                                                                                      |
|-----------------------------------|----------------------------------------------------------------------------------------------------------------------|
| <b>Substrate Temperature</b>      | +10°C min. / +30°C max.                                                                                              |
| <b>Ambient Temperature</b>        | +10°C min. / +30°C max.                                                                                              |
| <b>Material Temperature</b>       | Sikadur®-41 CF Normal must be applied at a temperatures between +10°C and +30°C.                                     |
| <b>Substrate Moisture Content</b> | When applied to mat moisture concrete, brush the adhesive well into substrate.                                       |
| <b>Dew Point</b>                  | <p>Beware of condensation!</p> <p>Substrate temperature during application must be at least 3°C above dew point.</p> |

### Application Instructions

|                    |                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                          |
|--------------------|--------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| <b>Mixing</b>      | <p>Part A : B : C = 2 : 1 : 2.5 by weight</p> <p>Part A : B : C = 2 : 1 : 3.4 by volume</p>                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                              |
| <b>Mixing Time</b> |  <p>Pre-batched units:<br/>Mix parts A+B together for at least 3 minutes with a mixing spindle attached to a slow speed electric drill (max. 600 rpm) until the material becomes smooth in consistency and a uniform grey colour. Then add part C and continue until mixture is homogeneous. Avoid aeration while mixing. Then, pour the whole mix into a clean container and stir again for approx. 1 more minute at low speed to keep air entrapment at a minimum. Mix only that quantity which can be used within its potlife.</p> |

| <b>Application Method / Tools</b>    | <p>When using a thin layer adhesive, apply the mixed adhesive to the prepared surface with a spatula, trowel, notched trowel, (or with hands protected by gloves).</p> <p>When applying as a repair mortar use some formwork.</p> <p>When using for bonding metal profiles onto vertical surfaces ,support and press uniformly using props for at least 12 hours, depending on the thickness applied (not more than 5 mm) and the room temperature.</p> <p>Once hardened check the adhesion by tapping with a hammer.</p>                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                       |              |        |        |               |              |              |
|--------------------------------------|---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|--------------|--------|--------|---------------|--------------|--------------|
| <b>Cleaning of Tools</b>             | <p>Clean all tools and application equipment with Thinner C immediately after use. Hardened / cured material can only be mechanically removed.</p>                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                              |              |        |        |               |              |              |
| <b>Potlife</b>                       | <p>Potlife (200 g) <span style="float: right;">(According to EN ISO 9514)</span></p> <table border="1" data-bbox="612 450 1528 544"> <thead> <tr> <th data-bbox="612 450 917 495">+10 °C</th> <th data-bbox="917 450 1222 495">+23 °C</th> <th data-bbox="1222 450 1528 495">+30 °C</th> </tr> </thead> <tbody> <tr> <td data-bbox="612 495 917 544">~ 180 minutes</td> <td data-bbox="917 495 1222 544">~ 60 minutes</td> <td data-bbox="1222 495 1528 544">~ 40 minutes</td> </tr> </tbody> </table> <p>The potlife begins when the resin and hardener are mixed. It is shorter at high temperatures and longer at low temperatures. The greater the quantity mixed, the shorter the potlife. To obtain longer workability at high temperatures, the mixed adhesive may be divided into portions. Another method is to chill parts A+B and C before mixing them (not below +5 °C).</p>                                                                                                                                                                                                                                                                                        | +10 °C       | +23 °C | +30 °C | ~ 180 minutes | ~ 60 minutes | ~ 40 minutes |
| +10 °C                               | +23 °C                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                          | +30 °C       |        |        |               |              |              |
| ~ 180 minutes                        | ~ 60 minutes                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                    | ~ 40 minutes |        |        |               |              |              |
| <b>Value Base</b>                    | <p>All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.</p>                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                               |              |        |        |               |              |              |
| <b>Local Restriction</b>             | <p>Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the product uses.</p>                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                  |              |        |        |               |              |              |
| <b>Health and Safety Information</b> | <p>For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.</p>                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                |              |        |        |               |              |              |
| <b>Legal Notes</b>                   | <p>The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.</p> |              |        |        |               |              |              |

## CE Labelling

|                                                                                       |                                                                 |
|---------------------------------------------------------------------------------------|-----------------------------------------------------------------|
| <b>CE</b>                                                                             |                                                                 |
| 0921                                                                                  |                                                                 |
| Sika Schweiz AG<br>Tueffenwies 16-22<br>CH - 8048 Zuerich<br>1001                     |                                                                 |
| 08                                                                                    |                                                                 |
| 0921-CPD-2053                                                                         |                                                                 |
| EN 1504-3                                                                             |                                                                 |
| Concrete repair product for non-structural repair<br>PC mortar (based on epoxy resin) |                                                                 |
| Compressive strength                                                                  | $\geq 45.0 \text{ N/mm}^2$                                      |
| Adhesive Bond:                                                                        | $\geq 2.0 \text{ N/mm}^2$                                       |
| Modulus of elasticity:                                                                | $< 15'000 \text{ N/mm}^2$                                       |
| Thermal compatibility part 1:                                                         | $\geq 2.0 \text{ MPa}$                                          |
| Coefficient of thermal expansion:                                                     | $3.5 \cdot 10^{-5}$                                             |
| Pot Life                                                                              | 60 min. at 20°C                                                 |
| Capillary absorption                                                                  | $\leq 0,5 \text{ kg} \cdot \text{m}^{-2} \cdot \text{h}^{-0,5}$ |
| Reaction to fire                                                                      | Euroclass E                                                     |
| Dangerous substances:                                                                 | (comply with 5.4) None                                          |

<sup>1)</sup> Last two digits of the year in which the marking was affixed

<sup>2)</sup> Identification number of the notified body

<sup>3)</sup> Number of the EC Certificate

<sup>4)</sup> Number of European standard



Sika Limited  
Watchmead  
Welwyn Garden City  
Hertfordshire  
AL7 1BQ  
United Kingdom

Phone +44 1707 394444  
Telefax +44 1707 329129  
[www.sika.co.uk](http://www.sika.co.uk), email: sales@uk.sika.com

