

Product Data Sheet
 Edition 14/07/2016
 Identification no:
 020703020030000002
 Sikadur®-Combiflex® CF Adhesive
 Type N

Sikadur®-Combiflex® CF Adhesive

Type N

2-part epoxy adhesive
 Part of the Sikadur®-Combiflex® System

Product Description

Sikadur®-Combiflex® CF Adhesive Type N is a thixotropic two part adhesives based on epoxy resins and fillers.

The Sikadur-Combiflex CF Adhesive Type N is part of the Sikadur®-Combiflex® System and used to glue the Sikadur®-Combiflex® Tape or the Sikadur®-Hypalon Strip to different substrates.

Type N (= Normal Potlife) is used for temperatures between +10°C to +30°C.

Uses As adhesive for the Sikadur®-Combiflex® System

- Characteristics / Advantages**
- Easy to mix and apply
 - Excellent adhesion to many materials
 - Styrene and nonylphenol free
 - Performs well within a wide temperature range
 - Completely weather and water resistant
 - Root resistant
 - Good resistance to many chemicals
 - Available with normal or rapid hardening grade adhesive
 - No primer needed
 - High mechanical resistance
 - Good abrasion resistance

Tests

Approval / Standards Testing according to EN 1504-4.

Product Data

Form

Colours

Part A:	White
Part B:	Dark grey
Part A+B mixed:	Light grey

Packaging

Pallets of 540 kg (90 sets)
 6 kg set (Part A: 4 kg, Part B: 2 kg)



Storage

Storage Conditions / Shelf Life 24 months from date of production if stored properly in unopened undamaged and sealed original packaging in dry conditions at temperatures between +5°C and +30°C.

Technical Data

Chemical Base Modified, solvent free, filled 2-part epoxy resin.

Density
~ 1.5 kg/l part A (at +23°C)
~ 1.5 kg/l part B Type N (at +23°C)
~ 1.5 kg/l part A+B mixed (at +23°C)

Thermal Expansion Coefficient *Linear expansion (1 / °C)*
Type Normal: $5.3 \times 10^{-5} (\pm 0.2 \times 10^{-5})$ at -20°C to +40°C (EN ISO 1770)

Service Temperature -30°C to +60°C

Mechanical / Physical Properties

Compressive Strength (ASTM D 695-96)

Curing time	Type Normal		
	+10°C	+23°C	+30°C
3 days	~ 35 N/mm ²	~ 48 N/mm ²	~ 52 N/mm ²
7 days	~ 41 N/mm ²	~ 50 N/mm ²	~ 54 N/mm ²
14 days	~ 43 N/mm ²	~ 54 N/mm ²	~ 55 N/mm ²

Bond Strength (DafSt-Richtlinie, Part 3)

Substrate	Bond strength
Concrete (dry)	> 4 N/mm ² (failure in concrete)
Concrete (mat moist / damp)	> 4 N/mm ² (failure in concrete)
Steel (blastcleaned)	> 10 N/mm ²

E-Modulus (ASTM D 695)

Temperature	E-Modulus (compressive)
+5°C	~ 4'200 N/mm ²
+23°C	~ 3'500 N/mm ²

Resistance

Chemical Resistance Please consult the Sikadur®-Combiflex® System product data sheet.

System Information

System Structure Please consult the Sikadur®-Combiflex® System product data sheet.

Application Details

Consumption Please consult the Sikadur®-Combiflex® System product data sheet.

Substrate Quality
Concrete, stone, mortar, rendering:
Substrate must be clean, free from oil, grease, laitance or loose particles.
Age of concrete 3 - 6 weeks dependent on environmental conditions.
Construction Steel 37:
Clean, free from oil, grease, rust and scale.

Substrate Preparation	<p><i>Concrete, stone, mortar, rendering:</i> Blastcleaning or equivalent mechanical means followed by thorough vacuum/dust removal.</p> <p><i>Construction Steel 37:</i> Blastcleaning or equivalent mechanical means followed by thorough vacuum/dust removal.</p> <p>Avoid dew point conditions for application.</p>
------------------------------	---

Application Conditions / Limitations

Substrate Temperature	Type Normal: +10°C to +30°C
Ambient Temperature	Type Normal: +10°C to +30°C
Material Temperature	Type Normal: +10°C to +30°C
Substrate Moisture Content	<p><i>Cementitious substrates:</i> Substrate must be dry or mat damp (no standing water) Brush the adhesive well into the substrate</p>
Dew Point	<p>Beware of condensation! Ambient temperature during application must be at least +3°C above dew point.</p>

Application Instructions

Mixing Part A : B = 2 : 1 parts by weight or volume

Pre-batched units:
Mix parts A+B together for at least 3 minutes with a mixing spindle attached to a slow speed electric drill (max. 300 rpm) until the material becomes smooth in consistency and a uniform grey colour. Avoid aeration while mixing. Then, pour the whole mix into a clean container and stir again for approx. 1 more minute at low speed to keep air entrapment at a minimum. Mix only that quantity which can be used within its potlife.



Application Method / Tools Please consult the Sikadur®-Combiflex® System product data sheet.

Cleaning of Tools Clean all tools and application equipment with Sika® Colma-Cleaner immediately after use. Hardened / cured material can only be mechanically removed.

Potlife

Potlife

Temperature	Type Normal (6 kg)
+5°C	-
+10°C	~ 125 minutes
+15°C	~ 95 minutes
+23°C	~ 50 minutes
+30°C	~ 25 minutes

If larger quantities are being mixed the temperature of Sikadur®-Combiflex® CF Adhesive will increase due to the chemical reaction, resulting in a reduced potlife.

Open time:

Type Normal: ~ 70 minutes at +23°C

Scratch resistance:

Temperature	Type Normal
+5°C	-
+10°C	~ 14 hours
+15°C	~ 10 hours
+23°C	~ 8 hours
+30°C	~ 6 hours

Waiting Time / Overcoating	Sikadur®-Combiflex® CF Adhesive may be overcoated with an epoxy coating. In this event do not smooth the adhesive with detergent. If waiting time between application of adhesive and overcoating is to be longer than 2 days, the adhesive must be blinded to excess with quartz sand immediately after application.
Notes on Application / Limitations	Please consult the Sikadur®-Combiflex® System product data sheet.
Value Base	All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.
Local Restrictions	Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.
Health and Safety Information	For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.
Legal Notes	The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.



SIKA LIMITED

Head Office · Watchmead · Welwyn Garden City · Hertfordshire · AL7 1BQ · United Kingdom
 Phone: +44 1 707 394444 · Fax: +44 1 707 329129 · www.sika.co.uk

