

Protective and anti-carbonation coatings

weber.cote smooth



Uses

- **weber.cote coatings** can be applied to most building materials, e.g.
 - concrete
 - blockwork
 - masonry
 - renders
- They are not recommended for common Fletton brickwork
- **weber.cote smooth** may be applied to brickwork for decorative purposes

About this product

The **weber.cote smooth** coating system provides excellent anti-carbonation protection with a minimum 15 years life expectancy. **weber.cote smooth** is both protective and decorative.

The system can be applied by brush, roller or spray.

This product has been formulated to comply with the requirements of BS EN 1504-2.

Features and benefits

- ▲ Excellent anti-carbonation coatings
- ▲ Durable – life expectancy in excess of 15 years
- ▲ Resistant to chloride ion ingress
- ▲ Coatings allow vapour diffusion
- ▲ This product has been formulated to comply with the requirements of BS EN 1504-2

Technical data

Anti-carbonation test results

The permeability values μ CO₂ are:

weber.cote smooth*	2.07 x 10 ⁶
---------------------------	------------------------

The μ CO₂ for good quality concrete is 400.

To protect concrete from carbonation, these coatings should be applied to clean, dry, sound substrates in a minimum two coat application to give a pinhole free surface. Porous or friable substrates should be treated with one coat of **weber.cote primer** prior to coating.

Water vapour diffusion

Both coatings are breathable, allowing moisture within the substrate to escape. Equivalent air layer thickness (max. 4 metres Klopfer)

weber.cote smooth	0.9 m
--------------------------	-------

*After 2000 hours weathering

Colours

weber.cote smooth is available in four standard colours. Specifiers should consult the Colour Charts, available on www.netweber.co.uk, and whenever possible, obtain samples prior to specification.

EU VOC regulations 2008

EU limit for weber.cote smooth (cat A/c): 75 g/l (2007)/40 g/l (2010). **weber.cote smooth** contains <35 g/l VOC.

weber.cote smooth

Preparation

If considered necessary, substrates should be primed with **weber.cote primer**.

New surfaces should be clean, sound and dry. Concrete must be free of coatings or mould oil and any laitance should be removed, following which the surface can be primed with **weber.cote primer**.

Old surfaces must also be clean, sound and dry. Glossy surfaces should be roughened to provide a key. Lichen, moss or fungal growth must be removed and the areas treated with **weber CL150** applied in accordance with the instructions on the data sheet*.

Chalky or friable surfaces, or previously decorated surfaces which are flaking, should be wire-brushed to remove loose materials and then stabilised by one coat of **weber.cote primer**.

* Full data sheet available from **Weber** on request.

Application

For complete protection, a two-coat application by brush, roller or spray is recommended.

Apply **weber.cote smooth** at a minimum of 150 µm wet film thickness per coat.

Depending on drying conditions and surface suction, the **weber.cote smooth** coating may be given a second coat in as little as 2 to 4 hours.

Do not apply below 4°C, when frost is expected or during rainfall.

Coverage

Coverage will depend on type of surface and porosity. The following is a guide for brush or roller application.

	Smooth surface	Medium roughness	Rough-cast
weber.cote smooth	8 to 10	7 to 8	5 to 6
weber.cote primer	7 to 10	5 to 7	4 to 5

weber.cote coatings should be applied in two coats for full anti-carbonation protection to concrete.

For major contracts, we suggest a site trial is carried out to determine actual coverages. **Figures below are m² per litre per coat.**

For spray application allow 10 – 15% extra material.

Packaging

All **weber.cote** coatings are supplied in 12.5 kg plastic containers. **weber.cote primer** is supplied in 5 litre plastic containers.

Storage and shelf life

Protect from frost. Store in clean, dry conditions between 5°C and 30°C. When stored in correct conditions a shelf life of 2 years can be expected.

Health and safety

Essentially non-hazardous.

Not harmful during normal use. After contact with skin, wash immediately with plenty of water. In case of contact with eyes, rinse immediately with plenty of water and seek medical advice. Keep out of the reach of children.

For further information, please request the Material Safety Data Sheet for this product.

Technical services

Weber's Customer Services Department has a team of experienced advisors available to provide on-site advice both at the specification stage and during application. Detailed specifications can be provided for specific projects or more general works. Site visits and on-site demonstrations can be arranged on request.

Technical helpline
Tel: 08703 330 070
e-mail: solutions@netweber.co.uk

Sales enquiries

Weber products are distributed throughout the UK through selected stockists and distributors. Please contact the relevant Customer Services Team below for all product orders and enquiries.

UK and Ireland
Tel: 08703 330 070
Fax: 0800 014 2995
e-mail: sales@netweber.co.uk

Saint-Gobain Weber Ltd
Dickens House, Enterprise Way, Maulden Road, Flitwick, Bedford MK45 5BY, UK
Tel: 08703 330 070 Fax: 0800 014 2995 e-mail: mail@netweber.co.uk
www.netweber.co.uk

To the best of our knowledge and belief, this information is true and accurate, but as conditions of use and any labour involved are beyond our control, the end user must satisfy himself by prior testing that the product is suitable for his specific application, and no responsibility can be accepted, or any warranty given by our Representatives, Agents or Distributors. Products are sold subject to our Standard Conditions of Sale and the end user should ensure that he has consulted our latest literature.